

Repositional Banner Self-adhesive 500

matt 8213 - 500 g/m²

Repositional self-adhesive banner consists of a polyester fabric laminated between two coatings of white vinly coated for use with solvent-based or UV curable inks. The special adhesive on the rear side makes it possible to reposition or reapply the print several times.

Advantages

- Excellent for presentations/ Exhibitions
- Suited for indoor & outdoor applications
- Very easy to apply; no bubbles, no wrinkles
- Suited for various surfaces such as glass, metal, untreated wood, PVC boards, stone slabs, etc.

Storage conditions

Shelf life: 3 years. Store in a cool, dry environment, free from direct sunlight. The adhesive side should always be fully covered with the original siliconised protective film. Please repack opened rolls for protection against dust and humidity. The rolls should be stored hanging from the core plugs inside the box otherwise striping may result.

Print Conditions

Best results are obtained between 15-25°C and 30-65% RH.

Environment, Health & Safety

No material safety datasheet required.

Outdoor use

Suited for outdoor use. The outdoor life will depend on substrate and exposure conditions. Also air pollution can affect outdoor life.

Lamination

Compatibility

Hot	Warm	Cold
1	1	1
3=excellen	2= fair	1= not recommended

Hot: heat activated: 105°C - 130°C
Warm: heat activated: 85°C - 95°C
Cold: presure sensitive

Colour Profiles

Sihl DI:rect b.v. develops high quality colour profiles for media / ink / printer / Rip combinations. Check availability of profiles for your printer at the download section www.sihl.nl or contact us at +31(0)73-6441044.

ING Bank 's-Bosch 67.47.92.742
BTW NL805593445B01
IBAN NL97 INGB 0674 7927 42
BIC/SWIFTCODE INGBNL2A

Op al onze aanbiedingen en overeenkomsten zijn de ICT-Office Voorwaarden van toepassing, gedeponeed d.d. 14 januari 2009 bij de Kamer van Koophandel te Midden-Nederland onder nummer 30174840. De afnemer heeft van deze voorwaarden kennis genomen en verklaart zich akkoord met de inhoud van deze voorwaarden. Op verzoek worden de ICT-Office Voorwaarden kosteloos nogmaals toegezonden.

Sihl Direct bv
Mangaan 8
5234 GD 's-HERTOGENBOSCH

telefoon +31(0)73 6441044
telefax +31(0)73 6441212
e-mail sihl@sihl.nl
internet www.sihl.nl
K.v.K. 's-Bosch 160.55.676

Solvent Ongecoat

Repositional Banner Self-adhesive 500matt 8213 - 500 g/m²

List of Printers

Printer	Ink	Quality
Océ CS6060/6100	Solvent	Excellent
Océ CS9065/9090 (low solvent)	Solvent	Excellent
Océ CS9065/9090 (eco solvent)	Solvent	Excellent
Océ CS7070/7075/7100	Solvent	Excellent
Océ Arizona series	Solvent	Excellent
Seiko color painter 64S / 100S	Solvent	Excellent
HP Designjet 8000s/9000s/10000s	Solvent	Excellent
Mutoh rockhopper (eco solvent ultra)	Solvent	Excellent
Mutoh spitfire (mild solvent)	Solvent	Excellent
Mutoh Toucan/Osprey/Phoenix	Solvent	Excellent
Agfa grand sherpa	Solvent	Excellent
ColorSpan display maker 72/98 UVX/UVR	Solvent	Excellent
ColorSpan display maker 72s/98s	Solvent	Excellent
Gandiinnovations Jeti 33xx/5000	Solvent	Excellent
Mimaki JV3 series	Solvent	Excellent
Roland Soljet/Versacam series	Solvent	Excellent
NUR, Scitex, Vutek	Solvent	Excellent

ING Bank 's-Bosch 67.47.92.742
 BTW NL805593445B01
 IBAN NL97 INGB 0674 7927 42
 BIC/SWIFTCODE INGBNL2A

Op al onze aanbiedingen en overeenkomsten zijn de ICT-Office Voorwaarden van toepassing, gedeponereerd d.d. 14 januari 2009 bij de Kamer van Koophandel te Midden-Nederland onder nummer 30174840. De afnemer heeft van deze voorwaarden kennis genomen en verklaart zich akkoord met de inhoud van deze voorwaarden. Op verzoek worden de ICT-Office Voorwaarden kosteloos nogmaals toegezonden.

Sihl Direct bv
 Mangan 8
 5234 GD 's-HERTOGENBOSCH

telefoon +31(0)73 6441044
 telefax +31(0)73 6441212
 e-mail sihl@sihl.nl
 internet www.sihl.nl
 K.v.K. 's-Bosch 160.55.676

Solvent Ongecoat

Repositional Banner Self-adhesive 500**matt 8213 - 500 g/m²****Physical Properties**

Weight	500 g/m ²	ISO 536	Tensile Strength*	> 1500/1400 N/5cm	SN EN ISO 1421
Thickness	370 µm	ISO 534	Elongation*	20/25 %	SN EN ISO 1421
Whiteness	91.22	D65/10	Tear Resistance*	> 100/100 N	SN EN 1875/T3
Dimensional Stability	< 0,5%		Opacity	93%	

*MD/CD

Available widths (mm)

3"Core

914

1372

The data provided in this product data sheet are values for orientation only.

Before using our print media please check their suitability for your printer and for your intended application. We do not take any liability for failures or damages resulting from technically modified printing inks and/or printers as technical specifications are subject to change.

ING Bank 's-Bosch 67.47.92.742
 BTW NL805593445B01
 IBAN NL97 INGB 0674 7927 42
 BIC/SWIFTCODE INGBNL2A

Op al onze aanbiedingen en overeenkomsten zijn de ICT-Office Voorwaarden van toepassing, gedeponereerd d.d. 14 januari 2009 bij de Kamer van Koophandel te Midden-Nederland onder nummer 30174840. De afnemer heeft van deze voorwaarden kennis genomen en verklaart zich akkoord met de inhoud van deze voorwaarden. Op verzoek worden de ICT-Office Voorwaarden kosteloos nogmaals toegezonden.

Sihl Direct bv
 Mangaan 8
 5234 GD 's-HERTOGENBOSCH

telefoon +31(0)73 6441044
 telefax +31(0)73 6441212
 e-mail sihl@sihl.nl
 internet www.sihl.nl
 K.v.K. 's-Bosch 160.55.676